



# 1436 Aluminium Foil Tape

---

## Product Data Sheet

---

Updated : June 2000  
Supersedes : July 1999

---

### Product Description

An aluminium foil combined with a rubber adhesive and an easy release liner designed for holding and sealing on a variety of surfaces. 1436 meets low flammability rating according to DIN 4102B1.

---

### Physical Properties

Not for specification purposes

<b>Adhesive Type</b>	Rubber
<b>Backing</b>	Soft Aluminium Foil
<b>Liner</b>	White Silicone Paper (Possible alternative : PE Film)
<b>Shelf Life</b>	12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity

---

### Performance

#### Characteristics

Not for specification purposes

<b>Adhesion to Steel</b> AFERA 4001	12 N/10mm	
<b>Tensile Strength</b> AFERA 4001	18 N/10mm	
<b>Elongation at Break</b> AFERA 4005	3.1 %	
<b>Total Tape Thickness</b>	0.075 mm	
<b>Water Vapour Transmission Rate</b>	<1.0 g/m <sup>2</sup> x 24 h	
<b>Flammability Rating</b> DIN 4102B1, Reference PA-111 2-216	B1	

Date : June 2000  
1436 Aluminium Foil Tape

---

### Additional Product Information

- Foil backing provides an excellent reflective surface for both heat and light
- Rubber adhesive bonds to many surfaces.
- Low water vapor transmission rate offers excellent sealing and patching performance.
- Best results obtained when applied to clean dry surfaces above 0 °C.
- Performance range –25 °C to +70 °C; short term +100 °C.

---

### Storage

Store in a dry location, out of direct sunlight and away from all sources of heat. Ideal conditions are 20 °C and 50% relative humidity. Storage in roll form for more than 12 months is not recommended.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



### Tapes & Adhesives Group

3M United Kingdom PLC  
3M House, PO Box 1,  
Market Place,  
Bracknell, Berkshire,  
RG12 1JU

Product Information :  
Tel 0870 60 800 50  
Fax 0870 60 700 99

3M Ireland  
3M House, Adelphi Centre,  
Upper Georges Street,  
Dun Laoghaire, Co. Dublin,  
Ireland

© 3M United Kingdom PLC 2000

Customer Service :  
Tel (01) 280 3555  
Fax (01) 280 3509