


Ferrite Components for the Electronics Industry

Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com



Fair-Rite Product's Catalog Part Data Sheet, 2773001112 Printed: 2013-07-03

190. 19001 TS







Part Number: 2773001112

Frequency Range: Lower Frequencies < 50 MHz (73 material)

Description: 73 BEAD ON LEAD

Application: Suppression Components

Where Used: Board Component

Part Type: Beads-on-Leads


Mechanical Specifications

Weight: .400 (g)

Part Type Information

Ferrite suppression beads are supplied assembled on tinned copper wire for automated circuit board assembly.

- -Parts with a '2' as the last digit of the part number are supplied taped and reeled per IEC 60286-1 and EIA RS-296-F standards. Taped and reeled parts are supplied 4500 pieces on a 14" reel. Taping details: Component pitch 5 mm. Inside tape spacing 52.5 mm. Tape width 6 mm.
- -Beads-on-leads can be supplied bulk packed. The last digit of bulk packed parts is a '1'.
- -Wires are oxygen free high conductivity copper with 100% matte tin plating over a nickel undercoating. The resistance of the wire is 3.5 mOhm for the 22 AWG and 2.2 mOhm for the 20 AWG wire.
- -Beads-on-leads are controlled for impedances only. Minimum impedance values are specified for the + marked frequencies. The minimum impedance is typically the listed impedance less 20%. The impedances of the 73 & 43 beads-on-leads are measured on the 4193A Vector Impedance Analyzer. The 61 beads-on-leads are tested for impedance on the 4291A RF Impedance Analyzer.
- -For any bead-on lead requirement not listed here, feel free to contact our customer service group for availability and pricing.
- -Our 'Bead-on-Lead Suppression Kit' (part number 0199000028) is available for prototype evaluation.
- -Explanation of Part Numbers: Digits 1&2 = product class, 3&4 = material grade and last digit 1 = bulk packed, 2 = taped and reeled.



Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 2773001112 Printed: 2013-07-03









Mechanical Specifications

Dim	mm	mm	nominal	inch
		tol	inch	misc.
Α	3.50	±0.25	0.138	
В	62.00	±1.50	2.440	
С	4.45	±0.25	0.175	-
D	0.65	-	-	22 AWG
E	-	-	-	-
F	-	-	-	-
G	-	-	-	-
Н			-	-
J			-	-
K	-	-	-	-

Electrical Specifications

Typical Impedance (Ω)		
1 MHz	12	
5 MHz	34	
10 MHz+	48	
25 MHz+	61	

Electrical Properties	

Land Patterns

V	W ref	Х	Υ	Z
-	-			

Winding Information

Turns	Wire	1st Wire	2nd Wire
Tested	Size	Length	Length
-	-	-	-

Reel Information

	Tape Width	Pitch	Parts 7 "	Parts 13 "	Parts 14 "
	mm	mm	Reel	Reel	Reel
Ī	6	5	-	-	4500

Package Size

Pkg Size
-
(-)

Connector Plate

# Holes	# Rows
-	-

Legend

+ Test frequency

Preferred parts, the suggested choice for new designs, have shorter lead times and are more readily available.

The column H(Oe) gives for each bead the calculated dc bias field in oersted for 1 turn and 1 ampere direct current. The actual dc H field in the application is this value of H times the actual NI (ampere-turn) product. For the effect of the dc bias on the impedance of the bead material, see figures 18-23 in the application note How to choose Ferrite Components for EMI Suppression.

A ½ turn is defined as a single pass through a hole.

∑I/A - Core Constant

A_e: Effective Cross-Sectional Area


 A_{I} - Inductance Factor $\left(\frac{L}{N^{2}}\right)$

I e: Effective Path Length

Ve: Effective Core Volume

NI - Value of dc Ampere-turns

N/AWG - Number of Turns/Wire Size for Test Coil



Fair-Rite Product's Catalog Part Data Sheet, 2773001112 Printed: 2013-07-03








Ferrite Material Constants

0.25 cal/g/°C Specific Heat 3.5 - 4.5 mW/cm - °C Thermal Conductivity Coefficient of Linear Expansion 8 - 10x10-6/°C 4.9 kgf/mm² Tensile Strength Compressive Strength 42 kgf/mm² 15x103 kgf/mm2 Young's Modulus Hardness (Knoop)..... 650 Specific Gravity $\approx 4.7 \text{ g/cm}^3$ The above quoted properties are typical for Fair-Rite MnZn and NiZn ferrites.

See next page for further material specifications.



Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

A MnZn ferrite, supplied only in small cores, to suppress conducted EMI frequencies below 50 MHz.

EMI suppression beads, beads on leads, SM beads, and multi-aperture cores are all available in 73 material.

Fair-Rite Product's Catalog Part Data Sheet, 2773001112

Printed: 2013-07-03








73 Material Characteristics:


Property	Unit	Symbol	Value
Initial Permeability © B < 10 gauss		μ_{i}	2500
Flux Density	gauss	В	3900
@ Field Strength	oersted	н	5
Residual Flux Density	gauss	B _r	1500
Coercive Force	oersted	H _o	0.24
Loss Factor	10-6	tan δ/μ;	10
@ Frequency	MHz		0.1
Temperature Coefficient of Initial Permeability (20 -70°C)	%/°C		0.65
Curie Temperature	°C	T _c	>160
Resistivity	Ωcm	ρ	1x10 ²

Complex Permeability vs. Frequency




Measured on a 2673000301 bead using the HP 4284A and the HP 4291A.

Initial Permeability vs. Temperature




Measured on a 17/10/6mm toroid at 10kHz.

Percent of Original Impedance vs. Temperature




Measured on a 2673000301 using the HP4291A.

Hysteresis Loop



Measured on a 17/10/6mm toroid at 10kHz.




Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 2773001112 Printed: 2013-07-03


ng). SO 9001 TS







Impedance, reactance, and resistance vs. frequency.



Impedance vs. frequency with dc bias.