KEMET Part Number: C0805X332K5RACAUTO



SMD Auto X7R Flex, Ceramic, 3300 pF, 10%, 50 VDC, X7R, SMD, MLCC, FT-CAP, Automotive Grade, 0805



| Dimensions | | |
|------------|------------------|--|
| Chip Size | 0805 | |
| L | 2mm +/-0.3mm | |
| W | 1.25mm +/-0.3mm | |
| Т | 0.78mm +/-0.20mm | |
| S | 0.75mm MIN | |
| В | 0.5mm +/-0.25mm | |

| Packaging Specifications | | |
|--------------------------|--------------------------|--|
| Packaging: | T&R, 180mm, Plastic Tape | |
| Packaging Quantity: | 4000 | |

| General Information | | |
|---------------------|--|--|
| Series: | SMD Auto X7R Flex | |
| Style: | SMD Chip | |
| Description: | SMD, MLCC, FT-CAP, Automotive Grade | |
| Features: | FT-CAP, Automotive Grade | |
| RoHS: | Yes | |
| Termination: | Flexible Termination | |
| Marking: | No | |
| Qualifications: | AEC-Q200 | |
| AEC-Q200: | Yes | |
| Component Weight: | 13 mg | |
| Shelf Life: | 78 Weeks | |
| MSL: | 1 | |

| Specifications | |
|---|--|
| Capacitance: | 3300 pF |
| Measurement Condition: | 1 kHz 1.0Vrms |
| Capacitance Tolerance: | 10% |
| Voltage DC: | 50 VDC |
| Dielectric Withstanding Voltage: | 125 VDC |
| Temperature Range: | -55/+125°C |
| Temperature Coefficient: | X7R |
| Capacitance Change with Reference to +25°C and 0 VDC Applied (TCC): | 15%, 1kHz 1.0Vrms |
| Dissipation Factor: | 2.5% 1 kHz 1.0Vrms |
| Aging Rate: | 3% Loss/Decade Hour: Referee Time is 1000 Hours |
| Insulation Resistance: | 100 GOhms |

Statements of suitability for certain applications are based on our knowledge of typical operating conditions for such applications, but are not intended to constitute - and we specifically disclaim - any warranty concerning suitability for a specific customer application or use. This Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by us with reference to the use of our products is given gratis, and we assume no obligation or liability for the advice given or results obtained.

