



SPECIFICATION

(Reference sheet)

· Supplier : Samsung electro-mechanics · Samsung P/N : CL21B222KBANNNC

· Product : Multi-layer Ceramic Capacitor · Description : CAP, 2.2nF, 50V, ±10%, X7R, 0805


A. Samsung Part Number

 CL
 21
 B
 222
 K
 B
 A
 N
 N
 N
 N
 C

 1
 2
 3
 4
 5
 6
 7
 8
 9
 10
 11

1	Series	Samsung Multi-layer Ceramic Capacitor					
2	Size	0805 (inch code)	L: 2.00	± 0.10 mm	W:	1.25 ± 0.10 m	m
3	Dielectric	X7R	8	Inner electrode		Ni	
4	Capacitance	2.2 nF		Termination		Cu	
(5)	Capacitance	±10 %		Plating		Sn 100%	(Pb Free)
	tolerance		9	Product		Normal	
6	Rated Voltage	50 V	10	Special		Reserved for	future use
7	Thickness	$0.65 \pm 0.10 \text{ mm}$	11)	Packaging		Cardboard Ty	ype, 7" reel

B. Structure & Dimension



Samsung P/N	Dimension(mm)					
Samsung F/N	L	W	Т	BW		
CL21B222KBANNNC	2.00 ± 0.10	1.25 ± 0.10	0.65 ± 0.10	0.50 +0.2/-0.3		

C. Samsung Reliablility Test and Judgement Condition

Tan δ (DF) 0.025 max. *A capacitor prior to measuring the capacitance is heat treated at 150°C+0/-10°C for 1 hour and maintained in ambient air for 24±2 hours. Rated Voltage 60~120 sec. Whichever is smaller Appearance No abnormal exterior appearance Microscope (×10) Withstanding No dielectric breakdown or mechanical breakdown Temperature Characteristics Adhesive Strength of Terminal electrode Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly Soldering Heat Tan δ, IR: initial spec. Within ±12.5% Amplitude: 1.5mm From 10liz to 56liz (return: 1min.) Zhours × 3 direction (x, y, z) Moisture Resistance Capacitance change: within ±12.5% Resistance Tan δ : 0.05 max IR: 500Mohm or 25Mohm × μF Whichever is smaller Temperature Resistance Resistance Capacitance change: within ±12.5% With 720% of the rated voltage Max. operating temperature Max. operating temperature Resistance Tan δ : 0.05 max IR: 1,000Mohm or 50Mohm × μF Whichever is smaller Temperature Capacitance change: within ±7.5% Toyloc condition		Judgement	Test condition			
Tan δ (DF) 0.025 max. treated at 150℃+0/-10℃ for 1 hour and maintained in ambient air for 24±2 hours. Insulation 10.000Mohm or 500Mohm×μF Rated Voltage 60~120 sec. Resistance Whichever is smaller Appearance Mo abnormal exterior appearance Microscope (×10) Withstanding No dielectric breakdown or wechanical breakdown 250% of the rated voltage Voltage mechanical breakdown Temperature X7R Characteristics (From-55℃ to 125℃, Capacitance change should be within ±15%) Adhesive Strength No peeling shall be occur on the of Termination terminal electrode Bending Strength Capacitance change : within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5℃, 32-0.3sec. (preheating : 80~120℃ for 10~30sec.) Resistance to Capacitance change : within ±7.5% Solder pot : 270±5℃, 10±1sec. Soldering Heat Tan δ, IR : initial spec. Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Wibration Test Capacitance change : within ±12.5% With rated voltage 40±2℃, 90~95%RH, 500+12/-0hrs Resistance Tan δ : 0.05 max IR : initial spec. Within ±12.5%	Capacitance	Within specified tolerance	1kl½ ±10% / 1.0±0.2Vrms			
Resistance Whichever is smaller Appearance No abnormal exterior appearance Microscope (×10)	Tan δ (DF)	0.025 max.	treated at 150 ℃+0/-10 ℃ for 1 hour and maintained in			
Appearance No abnormal exterior appearance Microscope (×10) Withstanding No dielectric breakdown or mechanical breakdown 250% of the rated voltage Temperature X7R Characteristics (From-55℃ to 125℃, Capacitance change should be within ±15%) Adhesive Strength No peeling shall be occur on the terminal electrode 500g·f, for 10±1 sec. Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0cu0.5 solder 245±5℃, 3±0.3sec. (preheating: 80~120℃ for 10~30sec.) Resistance to Capacitance change: within ±7.5% Solder pot: 270±5℃, 10±1sec. Soldering Heat Tan δ, IR: initial spec. Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) Wibration Test Capacitance change: within ±12.5% With rated voltage 40±2℃, 90~95%RH, 500+12/-0hrs Resistance Tan δ: 0.05 max IR: 500Mohm × μF Whichever is smaller With 200% of the rated voltage Max. operating temperature High Temperature Capacitance change: within ±12.5% With 200% of the rated voltage Max. operating temperature Max. operating temperature Temperature Capacitance change: within ±7.5% 1 cycle c	Insulation 10,000Mohm or 500Mohm×µF		Rated Voltage 60~120 sec.			
Withstanding No dielectric breakdown or mechanical breakdown 250% of the rated voltage Temperature X7R Characteristics (From-55 ℃ to 125 ℃, Capacitance change should be within ±15%) Adhesive Strength No peeling shall be occur on the terminal electrode 500g·f, for 10±1 sec. Bending Strength Capacitance change : within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.) Resistance to Capacitance change : within ±7.5% Solder pot : 270±5°C, 10±1sec. Soldering Heat Tan δ, IR : initial spec. Amplitude : 1.5mm From 10½ to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Wibration Test Capacitance change : within ±12.5% Amplitude : 1.5mm From 10½ to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Moisture Capacitance change : within ±12.5% With rated voltage Resistance Tan δ : 0.05 max Within ±12.5% Within ±12.5% With 200% of the rated voltage Max. operating temperature Max. operating temperature Max. operating temperature Temperature Capacitance change : within ±7.5% 1 cycle conditio	Resistance	Whichever is smaller				
Voltage mechanical breakdown Temperature X7R Characteristics (From-55℃ to 125℃, Capacitance change should be within ±15%) Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g·f, for 10±1 sec. Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating: 80~120°C for 10~30sec.) Resistance to Capacitance change: within ±7.5% Solder pot: 270±5°C, 10±1sec. Soldering Heat Tan δ, IR: initial spec. Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) Wibration Test Capacitance change: within ±12.5% With rated voltage Moisture Capacitance change: within ±12.5% With rated voltage Resistance Tan δ: 0.05 max With 200% of the rated voltage High Temperature Capacitance change: within ±12.5% Wax. operating temperature Resistance Tan δ: 0.05 max Max. operating temperature Whichever is smaller Monotherer is s	Appearance	No abnormal exterior appearance	Microscope (×10)			
Temperature Characteristics (From-55°C to 125°C, Capacitance change should be within ±15%) Adhesive Strength of Termination Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly Capacitance change: within ±7.5% Solder pot: 270±5°C, 10±1sec. Soldering Heat Vibration Test Capacitance change: within ±5% Tan δ, IR: initial spec. Capacitance change: within ±12.5% Tan δ : 0.05 max IR: 500Mohm or 25Mohm × Whichever is smaller High Temperature Resistance Tan δ : 0.05 max IR: 1,000Mohm or 50Mohm × Whichever is smaller Temperature Capacitance change: within ±7.5% With 200% of the rated voltage Max. operating temperature Max. operating temperature Max. operating temperature Tan δ, IR: initial spec. Tan δ, IR: initial spec. Tan δ, IR: initial spec. Tan δ : 0.05 max IR: 1,000Mohm or 50Mohm × Whichever is smaller Temperature Capacitance change: within ±7.5% With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs Max. operating temperature 1000+48/-0hrs Tan δ, IR: initial spec.			250% of the rated voltage			
Temperature Characteristics (From-55°C to 125°C, Capacitance change should be within ±15%) Adhesive Strength of Termination Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly Capacitance change: within ±7.5% Solder pot: 270±5°C, 10±1 sec. (preheating: 80~120°C for 10~30sec.) Resistance to Capacitance change: within ±7.5% Solder pot: 270±5°C, 10±1 sec. Soldering Heat Tan δ, IR: initial spec. Vibration Test Capacitance change: within ±5% Tan δ, IR: initial spec. Capacitance change: within ±12.5% Tan δ : 0.05 max IR: 500Mohm or 25Mohm × Whichever is smaller High Temperature Resistance Tan δ: 0.05 max IR: 1,000Mohm or 50Mohm × Whichever is smaller Temperature Capacitance change: within ±7.5% With 200% of the rated voltage Max. operating temperature Max. operating temperature 1000+48/-0hrs Whichever is smaller Temperature Capacitance change: within ±7.5% Tan δ, IR: initial spec. Vibration Test Tan δ : 0.05 max IR: 1,000Mohm or 50Mohm × Whichever is smaller Temperature Capacitance change: within ±7.5% With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs Max. operating temperature 1000+48/-0hrs Whichever is smaller Temperature Capacitance change: within ±7.5% Tan δ, IR: initial spec. Tan δ in 125°C	Voltage	mechanical breakdown				
Adhesive Strength of Termination Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly Capacitance change: within ±7.5% Soldering Heat Vibration Test Capacitance change: within ±12.5% Moisture Resistance Capacitance change: within ±12.5% Tan δ: 0.05 max IR: 500Mohm or 25Mohm × μF Whichever is smaller High Temperature Capacitance change: within ±7.5% Whichever is smaller Temperature Capacitance change: within ±7.5% Tan δ, IR: initial spec. With 200% of the rated voltage Max. operating temperature Max. operating temperature Capacitance change: within ±7.5% Whichever is smaller Temperature Capacitance change: within ±7.5% Whichever is smaller Temperature Capacitance change: within ±7.5% Tan δ, IR: initial spec. Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs Whichever is smaller Temperature Capacitance change: within ±7.5% Tan δ, IR: initial spec. Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs Max. operating temperature 1000+48/-0hrs With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs Whichever is smaller Temperature Capacitance change: within ±7.5% Tan δ, IR: initial spec.		X7R				
Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g·f, for 10±1 sec. Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating: 80~120°C for 10~30sec.) Resistance to Capacitance change: within ±7.5% Solder pot: 270±5°C, 10±1sec. Soldering Heat Tan δ, IR: initial spec. Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) Wibration Test Capacitance change: within ±12.5% With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs Resistance Tan δ: 0.05 max IR: 500Mohm or 25Mohm × μF Whichever is smaller With 200% of the rated voltage Max. operating temperature High Temperature Capacitance change: within ±12.5% Whichever is smaller Max. operating temperature Max. operating temperature Temperature Capacitance change: within ±7.5% Whichever is smaller 1 cycle condition Min. operating temperature → 25°C	Characteristics	(From-55℃ to 125℃, Capacitance change s	should be within ±15%)			
Bending Strength Capacitance change : within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.) Resistance to Capacitance change : within ±7.5% Solder pot : 270±5°C, 10±1sec. Soldering Heat Tan δ, IR : initial spec. Amplitude : 1.5mm Vibration Test Capacitance change : within ±5% Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Moisture Capacitance change : within ±12.5% With rated voltage Resistance Tan δ : 0.05 max IR : 500Mohm or 25Mohm × μF Whichever is smaller With 200% of the rated voltage High Temperature Capacitance change : within ±12.5% Whichever is smaller With 200% of the rated voltage Tan δ : 0.05 max IR : 1,000Mohm or 50Mohm × μF Whichever is smaller 1000+48/-0hrs Temperature Capacitance change : within ±7.5% Whichever is smaller 1 cycle condition Temperature Capacitance change : within ±7.5% Min. operating temperature → 25°C	Adhesive Strength					
with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.) Resistance to Capacitance change : within ±7.5% Solder pot : 270±5°C, 10±1sec. Soldering Heat Tan δ, IR : initial spec. Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Moisture Capacitance change : within ±12.5% With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs Resistance Tan δ : 0.05 max IR : 500Mohm or 25Mohm × /μ² Whichever is smaller With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs High Temperature Capacitance change : within ±12.5% Whichever is smaller With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs Temperature Capacitance change : within ±7.5% Whichever is smaller To cycle condition Min. operating temperature → 25°C	of Termination	terminal electrode				
Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.) Resistance to Capacitance change : within ±7.5% Solder pot : 270±5°C, 10±1sec. Soldering Heat Tan δ, IR : initial spec. Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Moisture Capacitance change : within ±12.5% With rated voltage Resistance Tan δ : 0.05 max IR : 500Mohm or 25Mohm × μF With rated voltage Whichever is smaller With 200% of the rated voltage High Temperature Capacitance change : within ±12.5% With 200% of the rated voltage Resistance Tan δ : 0.05 max IR : 1,000Mohm or 50Mohm × μF With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs Whichever is smaller 1 cycle condition Temperature Capacitance change : within ±7.5% 1 cycle condition Cycling Tan δ, IR : initial spec. 1 cycle condition Min. operating temperature → 25°C	Bending Strength	Capacitance change: within ±12.5%	Bending to the limit (1mm)			
is to be soldered newly 245±5°C, 3±0.3sec. (preheating: 80~120°C for 10~30sec.)			with 1.0mm/sec.			
is to be soldered newly 245±5°C, 3±0.3sec. (preheating: 80~120°C for 10~30sec.)	Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder			
Resistance to Capacitance change : within $\pm 7.5\%$ Solder pot : $270\pm 5^{\circ}$ C, 10 ± 1 sec. Vibration Test Capacitance change : within $\pm 5\%$ Amplitude : 1.5 mm From 10 Hz to 55 Hz (return : 1 min.) 2hours $\times 3$ direction (x, y, z) Moisture Capacitance change : within $\pm 12.5\%$ With rated voltage ± 1.5 With r		is to be soldered newly	245±5°C, 3±0.3sec.			
Soldering HeatTan δ, IR : initial spec.Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)MoistureCapacitance change : Tan δ : 0.05 maxwithin ±12.5% 40±2°C, 90~95%RH, 500+12/-0hrsHigh TemperatureCapacitance change : Whichever is smallerwithin ±12.5% 40±2°C, 90~95%RH, 500+12/-0hrsHigh TemperatureCapacitance change : With ±12.5%With 200% of the rated voltage Max. operating temperatureResistanceTan δ : Uncompared to 0.05 max IR : Whichever is smallerMax. operating temperature 1000+48/-0hrsTemperatureCapacitance change : Whichever is smaller1 cycle condition Min. operating temperatureTemperatureCapacitance change : Whithial spec.1 cycle condition Min. operating temperature			(preheating : 80~120°C for 10~30sec.)			
Vibration TestCapacitance change : within ± 5% Tan δ, IR : initial spec.Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z)MoistureCapacitance change : within ±12.5% Tan δ : 0.05 max IR : 500Mohm or 25Mohm × μ F Whichever is smallerWith rated voltage 40±2°C, 90~95%RH, 500+12/-0hrsHigh TemperatureCapacitance change : within ±12.5% Whichever is smallerWith 200% of the rated voltage Max. operating temperature 1000+48/-0hrsResistanceTan δ : 0.05 max Whichever is smallerMax. operating temperature 1000+48/-0hrsTemperatureCapacitance change : within ±7.5% Whichever is smaller1 cycle condition Min. operating temperatureTemperatureCapacitance change : within ±7.5% Min. operating temperature1 cycle condition Min. operating temperature	Resistance to	Capacitance change : within ±7.5%	Solder pot : 270±5°C, 10±1sec.			
Tan δ , IR: initial spec. From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) Moisture Resistance Tan δ : 0.05 max IR: 500Mohm or 25Mohm × μ F Whichever is smaller High Temperature Resistance Tan δ : 0.05 max IR: 500Mohm or 25Mohm × μ F Whichever is smaller High Temperature Resistance Tan δ : 0.05 max IR: 1,000Mohm or 50Mohm × μ F Whichever is smaller Temperature Capacitance change: within $\pm 12.5\%$ With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs Temperature Capacitance change: within $\pm 7.5\%$ Temperature Capacitance change: within $\pm 7.5\%$ Toycle condition Min. operating temperature \rightarrow 25°C	Soldering Heat					
Resistance Tan δ : 0.05 max $40\pm2^{\circ}$ C, $90\sim95\%$ RH, $500\pm12/-0$ hrs IR : 500Mohm or 25Mohm × μF Whichever is smaller High Temperature Capacitance change : within ±12.5% With 200% of the rated voltage Resistance Tan δ : 0.05 max Max. operating temperature IR : 1,000Mohm or 50Mohm × μF 1000+48/-0hrs Whichever is smaller 1 cycle condition Temperature Capacitance change : within ±7.5% 1 cycle condition Cycling Tan δ, IR : initial spec. Min. operating temperature → 25°C	Vibration Test	, ,	From 10Hz to 55Hz (return : 1min.)			
IR: 500Mohm or 25Mohm × μ F Whichever is smaller High Temperature Resistance Tan δ: 0.05 max IR: 1,000Mohm or 50Mohm × μ F Whichever is smaller Temperature Capacitance change: within ±7.5% With 200% of the rated voltage Max. operating temperature 1000+48/-0hrs Temperature Capacitance change: within ±7.5% Tan δ, IR: initial spec. 1 cycle condition Min. operating temperature \rightarrow 25°C	Moisture	Capacitance change: within ±12.5%	With rated voltage			
Whichever is smallerHigh Temperature ResistanceCapacitance change : within $\pm 12.5\%$ Tan δ : 0.05 max IR : 1,000Mohm or 50Mohm × μ F Whichever is smallerWith 200% of the rated voltage Max. operating temperature 1000+48/-0hrsTemperature CyclingCapacitance change : within $\pm 7.5\%$ Tan δ , IR : initial spec.1 cycle condition Min. operating temperature	Resistance	Tan δ: 0.05 max	40±2°C, 90~95%RH, 500+12/-0hrs			
High Temperature ResistanceCapacitance change : within $\pm 12.5\%$ Tan δ : 0.05 max IR : 1,000Mohm or 50Mohm × μ F Whichever is smallerWith 200% of the rated voltage Max. operating temperature 1000+48/-0hrsTemperature CyclingCapacitance change : within $\pm 7.5\%$ Tan δ , IR : initial spec.1 cycle condition Min. operating temperature		IR: 500Mohm or 25Mohm × μ F				
Resistance Tan δ : 0.05 max Max. operating temperature IR : 1,000Mohm or 50Mohm × μ F 1000+48/-0hrs Whichever is smaller 1 cycle condition Cycling Tan δ, IR : initial spec. Min. operating temperature Max. operating temperature 1000+48/-0hrs 1 cycle condition 1 cycle condition Min. operating temperature → 25°C		Whichever is smaller				
IR: 1,000Mohm or 50Mohm × μ F Whichever is smaller Temperature Capacitance change: within ±7.5% 1 cycle condition Tan δ, IR: initial spec. 1 cycle condition Min. operating temperature \rightarrow 25°C	High Temperature	Capacitance change: within ±12.5%	With 200% of the rated voltage			
	Resistance	Tan δ: 0.05 max	Max. operating temperature			
Temperature Capacitance change : within $\pm 7.5\%$ 1 cycle condition Cycling Tan δ, IR : initial spec. Min. operating temperature \rightarrow 25°C		IR: 1,000Mohm or 50Mohm × μ F	1000+48/-0hrs			
Cycling Tan δ, IR : initial spec. Min. operating temperature → 25°C		Whichever is smaller				
	Temperature	Capacitance change : within ±7.5%	1 cycle condition			
→ Max. operating temperature → 25°C	Cycling	Tan δ, IR : initial spec.	Min. operating temperature → 25°C			
			→ Max. operating temperature → 25°C			
5 cycle test			5 cycle test			

X The reliability test condition can be replaced by the corresponding accelerated test condition.

D. Recommended Soldering method:

Reflow (Reflow Peak Temperature : 260+0/-5°C, 10sec. Max)



A Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.

Disclaimer & Limitation of Use and Application

The products listed in this Specification sheet are **NOT** designed and manufactured for any use and applications set forth below.

Please note that any misuse of the products deviating from products specifications or information provided in this Spec sheet may cause serious property damages or personal injury.

We will **NOT** be liable for any damages resulting from any misuse of the products, specifically including using the products for high reliability applications as listed below.

If you have any questions regarding this 'Limitation of Use and Application', you should first contact our sales personnel or application engineers.

- ① Aerospace/Aviation equipment
- 2 Automotive or Transportation equipment (vehicles, trains, ships, etc)
- 3 Medical equipment
- 4 Military equipment
- ⑤ Disaster prevention/crime prevention equipment
- 6 Power plant control equipment
- Atomic energy-related equipment
- Undersea equipment
- Traffic signal equipment
- Data-processing equipment
- ## Electric heating apparatus, burning equipment
- Safety equipment
- ® Any other applications with the same as or similar complexity or reliability to the applications